

HumiSeal® UV500

UV Curable Conformal Coating

Technical Data Sheet

HumiSeal® UV500 is a high solids UV dual cure elastomeric acrylate conformal coating. HumiSeal® UV500 exhibits excellent flexibility, moisture resistance and electrical insulation properties as well as good chemical resistance.

HumiSeal® UV500 has been specifically developed to:

- Cure tack-free with microwave or arc UV light.
- Have a secondary cure mechanism that will fully cure any unexposed areas of the coating within 7 days at ambient conditions.
- Have a higher flexibility compared with other UV curable conformal coatings, giving improved performance in thermal cycling tests.
- Fluoresce under UV light to allow coating inspection.
- Be applied by all selective coating equipment.
- Have excellent chemical and moisture resistance.

HumiSeal® UV500 meets the following standards:

- IEC 60664-3
- Compliant to REACH, RoHS Directive EU 2015/863
- Compliant with China RoHS 2
- Compliant to China Standard GB30981-2020
- Recognized under UL File Number E105698

Properties of HumiSeal® UV500 Liquid Coating

Density	1.0 to 1.1 g/cm ³
Minimum Solids Content, % by weight	98%
Viscosity at 25°C	275 to 375 centipoise
Shelf Life at Room Temperature, DOM	9 Months*
Recommended UV Cure	See Curing Below

* Unless otherwise specified on material packaging

Properties of HumiSeal® UV500 Cured Coating

Coating Thickness, as recommended by IPC guidelines	25 - 125 microns
Coating Thickness, as recommended for application	75 - 130 microns
Time to reach optimum properties	7 days after UV cure
Glass Transition Temperature - DSC	-43°C
Coefficient of Thermal Expansion - TMA	137ppm/°C Below Tg 311ppm/°C Above Tg
Modulus – DMA	0.4MPa @ 25°C
Dielectric Withstand Voltage, per MIL-I-46058C	> 1500 V
Surface Insulation Resistance (per IPC J-STD-004 (mod.))	8.9 log ₁₀ ohms
Moisture Insulation Resistance, per MIL-I-46058C	1.6 x 10 ¹⁰ ohms
Flammability per UL94	V-0
Fungus Resistance, per IPC-TM-650 2.6.1.1	Pass
Thermal Conductivity	0.505 W/mK
Dielectric Constant at 10 GHz per ASTM D-2520	3.07

Insulation Resistance, per MIL-I-46058C
Surface Resistivity per ASTM D-257
Volume Resistivity per ASTM D-257

4.5×10^{11} ohms
 2.0×10^{11} ohms
 8.0×10^{12} ohm.cm

Application of HumiSeal® UV500

Conformal coatings can be successfully applied to substrates that have been cleaned prior to coating and also to substrates assembled with low residue, “no clean” assembly materials. Users should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials, process conditions and cleanliness level. Please contact HumiSeal® for additional information.

Spraying

HumiSeal® UV500 can be applied via standard selective coating equipment or by conventional hand spray equipment. The source air used for spraying must be dry (a dry inert gas (nitrogen or argon) is highly recommended) to prevent premature curing of the secondary cure mechanism. The spraying should be done with adequate ventilation so that the vapor and mist are carried away from the operator.

Brushing

HumiSeal® UV500 may be applied by brush for rework or touch up only. Brush must be cleaned with solvent promptly after use.

Curing

HumiSeal® UV500 is a highly crosslinked coating. In order to achieve maximum crosslinking density, the product must be exposed to the correct spectral output. HumiSeal® has modelled the performance of UV500 using Arc and Microwave based UV curing equipment. The table below outlines the required dosage and irradiance values necessary to render HumiSeal® UV500 tack free post UV exposure with both equipment types. Minimum figures should provide a tack free surface. The maximum recommendation represents highest tested values by Humiseal. The cure recommendations may change as curing technology develops.

		Dose J/cm2*			Irradiance W/cm2*		
		UVA	UVB	UVC	UVA	UVB	UVC
Min	Arc System	1.5	1.5	0.40	0.50	0.50	0.10
Min	Microwave System	2.0	2.0	0.40	0.70	0.70	0.15
Max	Arc System	2.8	2.7	0.80	0.90	0.80	0.20
Max	Microwave System	3.0	3.0	0.60	1.15	1.15	0.24

**Values measured with a Powerpuck II UV radiometer*

Heat is also an important component with UV cure, and different systems produce different heat outputs. Higher heat levels allow UV cure at lower dose/irradiance levels. Consequently, HumiSeal® recommend that curing is discussed with HumiSeal® Technical staff to ensure the exact customer process being used will meet the coating cure requirements. After UV exposure and return to room temperature the coating should be tack free.

HumiSeal® UV500 contains a reliable secondary moisture cure mechanism which will cure any shadow areas on the assembly within 7 days at ambient moisture.

HumiSeal® UV500 was designed to be cured using a microwave UV oven equipped with an “H” style bulb. Arc systems can cure HumiSeal® UV500 however care must be taken during the equipment selection process to ensure minimum dosage and irradiance values obtained will properly cure the coating. Because of the variations possible in curing equipment type and configuration, it is strongly recommended that you contact HumiSeal® Technical Support to discuss your equipment and process in detail.

Clean Up

To flush equipment and clean uncured HumiSeal® UV500, non-alcohol based solvents should be used. HumiSeal® Thinner 521 or Thinner 521EU is recommended.

Rework

HumiSeal® UV500 is a highly crosslinked UV cured coating. The cured film has a high degree of environmental and chemical resistance and will be more difficult to remove than traditional conformal coatings. Thermal displacement and mechanical abrasion are suitable options for rework of HumiSeal® UV500.

Storage

HumiSeal® UV500 is photosensitive. The product should not be exposed to direct sunlight or full spectrum fluorescent lighting. HumiSeal® UV500 should be stored cool below 20°C, to maximize shelf life. Prior to use, allow the product to equilibrate for 24 hours at room temperature. HumiSeal® UV500 is a moisture curing material and care should be taken to protect process vessels and partial containers from moisture. Partial containers must be purged with a dry, inert gas such as dry air, nitrogen or argon before closure, otherwise premature polymerization by atmospheric moisture will occur.

Caution

Application of HumiSeal® Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult SDS prior to use.

Contact HumiSeal®

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal India

J-154, M.I.D.C Bhosari
Pune 411 026
Maharashtra
India
Tel: +91 20 66308098
indiatechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.