

## FTH

### Fast Dry Thinner

FTH is a high purity solvent blend designed for use with Electrolube's fast drying conformal coatings, AFA and PUCAF. The primary use of FTH is to dilute the coating for use in dip and spray coating applications.

<b>Approvals</b>	<b>RoHS-2 Compliant (2011/65/EU):</b>	<b>Yes</b>
<b>Liquid Properties</b>	Appearance	Clear, Colourless liquid
	Flash Point:	27°C
	Density @ 20°C (g/ml):	0.88
	VOC Content:	100%

<u>Description</u>	<u>Packaging</u>	<u>Order Code</u>	<u>Shelf Life</u>
Fast Dry Thinners	5 Litres Bulk	FTH05L	36 Months

### Directions for Use

#### Spray Coating

The optimum viscosity to give coating quality and thickness depends on the spray equipment and conditions, as well as the conformal coating chosen. Suitable spray viscosity is typically 40-70mPa s. In addition, extra solvent may need to be added to avoid immediate drying during application, commonly known as 'cobwebbing'. The thinned solution should be stirred thoroughly and allowed to stand. All air bubbles must be allowed time to disperse before attempting to spray. Thinners should be added gradually until the desired spray pattern and coating weight is achieved.

#### Dip Coating

FTH may be used to maintain the viscosity of AFA and PUCAF conformal coatings in open tanks used in dip coating processes. Over time, the solvent within the coatings evaporates. This increases the viscosity and produces a thicker coating. This solvent loss must be replaced to maintain the correct viscosity and provide an economical coating thickness. The amount of FTH to be added depends on the total volume of the tank, ambient temperature and rate of use. FTH should be added slowly, allowing the viscosity of the coating to alter prior to adding additional thinners. FTH is a flammable solvent blend and should be used in a well-ventilated area. All sources of ignition must be avoided. Please refer to the separate Health & Safety Data Sheet for further details.

#### Equipment Cleaning

FTH thinners may also be used to clean metal equipment found in the coating process including but not limited to spray guns and dip coating machinery.

Revision 1: Oct 2013